



ADVANCED REFINISH COMPONENTS

Technical Data Sheet

ARC EURO CLEAR

DESCRIPTION:

ARC 31580 is a High Solids European Clearcoat that works well in air dry or baking applications. ARC 31580 retains excellent gloss and durability.

PRODUCT & ADDITIVES:

PRODUCT	ITEM #	SIZE
Euro Clear	31580	5 L
Euro Clear Activator Fast	31510	2.5 L
Euro Clear Activator Medium	31520	2.5 L
Euro Clear Activator Slow	31530	2.5 L

COMPATIBLE SUBSTRATES:

ARC Euro Clear can be applied over any acrylic or polyester basecoat.

SAFETY ASPECTS:


Users should review the Safety Data Sheet (MSDS) and product label for the material to be used to determine possible health hazards, appropriate engineering controls and precautions to be observed in the use of the material. Copies of the SDS and product label are available upon request.

MIXING RATIOS:

2 parts ARC Euro Clear
1 part ARC Euro Clear Activator; Fast, Medium, or Slow


GUN SETUP:


TYPE	FLUID TIP	SPRAYING PRESSURE
Conventional Gravity:	1.3 mm - 1.6 mm	35 - 45 psi @ gun
Siphon	1.4 mm - 1.8 mm	35 - 45 psi @ gun
HVLP Gravity	1.3 mm - 1.4 mm	8 - 10 psi @ gun

NUMBER OF COATS:

2 full wet coats

FLASH TIMES:

5 to 10 minutes at 75°F / 24°C with medium hardener.

PURGE TIMES:

10 minutes @75°F (24°C).

DRYING TIMES:


METAL TEMP	DRY TIME
75°F (24°C)	6 to 8 hours
140°F (60°C)	30 minutes



ADVANCED REFINISH COMPONENTS

Technical Data Sheet

ARC EURO CLEAR

RECOATABILITY:	ARC Euro Clear may be recoated after bake cycle when metal has completely cooled down. For best results in air dry situations wait over night.
FILM THICKNESS:	Approximately 1.0 mil per coat (DFT)
DRY TO POLISH:	Air Dry: 6 - 8 hours @ 75°F Force Dry: After cool down
DECALS:	Decals, lettering or stripes can be applied after 24 hours.
CLEANING EQUIPMENT:	Clean equipment immediately with ARC lacquer thinner.

TECHNICAL DATA:



Color	Clear	
Activator/Hardener	ARC Euro Clear Activator	
Mix Ratio	2:1	
Pot Life	1 hour @ 68-75°F (20-24°C)	
Number of Coats	2 full wet coats	
Flash Time	5 - 10 minutes @75°F (24°C)	
Purge Time	10 minutes @75°F (24°C)	
Dry Time	Air Dry	6 - 8 hours @75°F (24°C)
	Force Dry	30 mins @ 140°F (60°C)
Gun Set Up	Refer to table on page 1	
Air Pressure at Gun	Refer to table on page 1	
Regulatory V.O.C.	4.41 lbs/gal (505 g/l)	
Actual V.O.C.	3.88 lbs/gal (464 g/l)	
Sprayable V.O.C.	4.4 lbs/gal (527 g/l)	
% Solids RTS by weight	40.5%	
Package Size	5 Liter	
Number per Case	2	
Shelf Life	12 months unopened	

All data given below are MAXIMUM THEORETICAL VALUES based on the product AS CURRENTLY FORMULATED. Variations may occur on individual batches due to adjustments made during production.

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data subject to change as Autokote Systems, LLC deems appropriate.